



Technical Data

PP1BEP		SPECIFICATION	
ITEMS	UNIT	SPEC VALUES	TEST METHOD
<i>Dimension & Tolerances</i>			
Thickness	mm	0.035±10%	ASTM D-1000
Inside Diameter of Roll	mm	77±1	
Weight Composition	g/m ²		
Backing		BOPP	
Thickness	mm	0.023	ASTM D-1000
Glue		ACRYLIC BASE	
Physical & Chemical Prop		(UV Resistance)	
180° Peel Adhesion To Steel	kgf/25mm	0.50 ~ 1.0	ASTM D-1000
Unwind Force	kgf/25mm	0.10 ~ 0.35	ASTM D-1000
Tensile Strength	kgf/25mm	7.5 ↑	
Elongation	%	100↑	
Storage Condition		23 ^o C. 65%R.H	
Remark:			
Test Condition: ASTM D-1000			
Storage period: 12 months after the date of manufacturing 23±2°C & 65 ± 5% R.H.			
The information above is reference only and should not be as inspection standard			
Customers need to test and confirm products for the actual operational requirement and purpose or inform us to supply the further introduction and service.			

Important Notice to Purchaser

All statement, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and users assume all risk and liability whatsoever in connection therewith.

No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.

FOUR PILLARS ENTERPRISE CO., LTD.

No. 12, Lane 61, Sec. 1, Kuang Fu Rd, San Chung City, 241 Taipei, Taiwan, R.O.C

TEL: 886-2-2999-1133 FAX: 886-2-2999-1136 or 2999-2284 <http://www.fourpillars.com.tw>